



RITELOK GASKET MAKERS

FLEXIBLE, TOUGH
POLYMER GASKETS

HAND APPLICABLE
SCREEN PRINTABLE
ROBOTIC APPLICATIONS

RiteLok gasket makers create formed-in-place gaskets on flanges and housings, eliminating the need for large inventories of pre-cut gaskets. Once cured, the product keys into the adjacent faces of the joint. RiteLok gasket makers will not relax or shrink and have exceptional pressure and solvent resistance, such as petroleum solvents.



PRODUCT	SIZE (quantity)	ITEM #	TYPICAL USE	COLOR	GAP FILL UNPRIMED (PRIMED)	VISCOSITY (cP's)	CURED STATE	TEMP. RANGE	CURE SPEED UNPRIMED (PRIMED)
GM 04	50mL (10/case)	GM04-50	Formulated to seal gaps to .03" and provide an instant low pressure seal.	orange	.03" / .75 mm (.05" / 1.25 mm)	200,000 500,000 thixo	rigid	-65°F – 300°F (-54°C – 150°C)	4 – 24 hours (30 min – 4 hours)
	250mL (2/case)	GM04-250							
	300mL (each)	GM04-300							
GM 10	50mL (10/case)	GM10-50	Can be screen printed. Used in rigid assemblies for making or dressing gaskets.	red	.01" / .25 mm (.02" / .5 mm)	165,000 500,000 thixo	rigid	-65°F – 400°F (-54°C – 200°C)	4 – 24 hours (30 min – 4 hours)
	250mL (2/case)	GM10-250							
	300mL (2/case)	GM10-300							
GM 15	50mL (10/case)	GM15-50	General purpose flexible gasket maker. Withstands vibration. Gearbox covers, pump flanges, fuel and water pumps.	purple	.01" / .25 mm (.05" / 1.25 mm)	275,000 950,000 thixo	flexible	-65°F – 300°F (-54°C – 150°C)	1 – 12 hours (15 min – 2 hours)
	250mL (2/case)	GM15-250							
	300mL (2/case)	GM15-300							
GM 18	50mL (10/case)	GM18-50	Formulated for mating aluminum flanges. Provides an instant seal without the use of a primer.	red	.01" / .25 mm (.05" / 1.25 mm)	750,000 3,750,000 thixo	flexible	-65°F – 300°F (-54°C – 150°C)	4 – 24 hours (30 min – 4 hours)
	250mL (2/case)	GM18-250							
	300mL (2/case)	GM18-300							



[THE CHEMISTRY OF EXCELLENCE]

RITELOK