

Vibra-TITE®

URETHANES

Vibra-Tite Urethanes are high strength adhesives for bonding wood, metal, glass, stone, ceramic, brick, fiberglass, carbon, foam and more.

- Ideal for industrial assembly and household repairs
- 100% Waterproof
- Temperature resistant
- Low foam formulations



Vibra-TITE® BONDING PRODUCTS

Vibra-Tite Part #	Available Sizes	Color	Viscosity	Specific Gravity	Mix Ratio	Cure Method	Work Life	Full Cure	Service Temp Range	Durometer	Overlap Shear Strength
801 URETHANE											
80105 80155 80175	5 Gallon Pail 55 Gallon Drum 275 Gallon Tote	Amber	5,000	1.13	1 Part	Moisture	25 - 30 minutes	24 hours	-20°F (-29°C) to 200°F (93°C)	Shore D 45-55	5 mm CRS, @ 750 psi
801FC URETHANE - FAST CURE											
80105FC 80155FC 80175FC	5 Gallon Pail 55 Gallon Drum 275 Gallon Tote	Amber	5,000	1.13	1 Part	Moisture	15 - 20 minutes	24 hours	-20°F (-29°C) to 200°F (93°C)	Shore D 45-55	5 mm CRS, @ 750 psi
801SS URETHANE - STAINLESS STEEL											
80105SS 80155SS 80175SS	5 Gallon Pail 55 Gallon Drum 275 Gallon Tote	Amber	5,000	1.13	1 Part	Moisture	25 - 30 minutes	24 hours	-20°F (-29°C) to 200°F (93°C)	Shore D 45-55	5 mm CRS, @ 750 psi
802 POLYURETHANE											
80205 80255 80275	5 Gallon Pail 55 Gallon Drum 275 Gallon Tote	Green	2,000	1.13	1:1	2-Component System	3 minutes - 2.5 hours	8-48 hours	-20°F (-29°C) to 200°F (93°C)	Shore D 45-55	5 mm AL. 2014-T3 @ 420 psi
989 POLYURETHANE											
98902 98904 98908 98916 98900	2 oz Bottle 4 oz Bottle 8 oz Bottle 16 oz Bottle 1 L	Amber	7,000	1.1	1 Part	Moisture	25 - 30 minutes	24 hours	-20°F (-29°C) to 200°F (93°C)	Shore D 45-55	5 mm CRS, @ 750 psi
989 DAM GOOD GLUE - POLYURETHANE											
98902DGG 98902BCDGG 98908DGG 98916DGG	2 oz Bottle 2 oz in Blister Card 8 oz Bottle 16 oz Bottle	Amber	7,000	1.1	1 Part	Moisture	25 - 30 minutes	24 hours	-20°F (-29°C) to 200°F (93°C)	Shore D 45-55	5 mm CRS, @ 750 psi

Note: 800 series urethanes can be customized to meet specific industrial needs.